




Robertson Street,  
Office Development, Glasgow



Kelvingrove, Art Gallery & Museum, Glasgow

**REFERENCE BUILDINGS:**

- Diglas Basin, British Waterways  
- Worcestershire
- Scottish Exhibition Centre - Glasgow
- Gretna Bridge - Gretna
- Fountain Square - Manchester
- Capitol Building - Albany New York
- Ashby Castle - Ashby de-la-Zouch
- Great St Helens - London
- Stag Place Piazza - London
- Chungwa Picture Tubes - Glasgow

**STONE TEST DATA: as tested at the BRE, Garston [www.bre.co.uk](http://www.bre.co.uk)**

Test Type	Norm	Result
Water Absorption	BSEN 13755	5.30%
Porosity	BSEN 1936	16.80%
Density		2034 Kg/m <sup>3</sup>
Abrasion Resistance	BSEN 1341:2000	32.0mm (Domestic)
Compressive Strength	BSEN 1926 (1999)	81 MPa
Slip Resistance	BSEN 1341:2000	Dry: 92 Wet: 79
Flexural Strength	BSEN 13161 (2001)	5.04 MPa
Durability	BSEN 1341:2001	Pass: Change in Flexural strength 6.7%
Acid Immersion	BRE 141	Fail

**TECHNICAL DETAILS:**

Geographical Type	Triassic, Sandstone
Main Colour	Terracotta Red
Colour Variations	Varigated Bed Markings, Occasional red and white deposit
Texture	Fine Grain
Availability	Contract up to 10,000 m <sup>2</sup>
Average Block Size	2000L x 1000W x 400Hmm
Suggested Ashlar Module Size	700L x 300H mm

Colours in this brochure are as accurate as the printing process allows and actual sight of the material is strongly recommended.

# COVE RED SANDSTONE

Quarried at Kirk Patrick Fleming in Southern Scotland, Cove Red is a fine-grained, warm terracotta coloured sandstone. The stone can have distinct bed markings, which gives it an interesting and unique characteristic. The material is suitable for most facades, monumental applications and also suitable for carving. Cove Red quarry has yielded many thousands of tonnes, employing up to 400 men at the turn of the century. This material has an enviable history and large quantities were and still are shipped to America and Canada.

## BLOCK



## STONE LIMITED

Bolehill Quarry, Wingerworth,  
Chesterfield, Derbyshire  
S42 6RG, England  
Tel: +44 (0)1246 554450  
Fax: +44 (0)1246 220095  
Email: [blockstone@realstone.co.uk](mailto:blockstone@realstone.co.uk)  
Web: [www.blockstone.co.uk](http://www.blockstone.co.uk)



## Realstone

**The Complete Natural Stone Service**

Head Office  
Realstone Limited  
Wingerworth, Chesterfield,  
Derbyshire S42 6RG, England  
Tel: +44 (0)1246 270244  
Fax: +44 (0)1246 220095  
Email: [sales@realstone.co.uk](mailto:sales@realstone.co.uk)  
Web: [www.realstone.co.uk](http://www.realstone.co.uk)

# COVE RED SANDSTONE