

BLOCK



STONE  
LIMITED

# BLOCK STONE LTD

HEAD OFFICE: Bolehill Quarry, Wingerworth,  
Chesterfield, Derbyshire. S42 6RG  
TEL: +44 (0)1246-554450 FAX: +44 (0)1246-220095  
E-mail:- [blockstone@realstone.co.uk](mailto:blockstone@realstone.co.uk)  
Web site:- <http://www.blockstone.co.uk>

## Swaledale Limestone



### Specifying the stone

Quarry details: Melsonby Quarry, Barton, Nr Richmond, North Yorkshire  
Supplier: Block Stone Ltd, Bolehill Lane, Wingerworth, Chesterfield, Derbyshire,  
S42 6RG, England  
Block Sales: Block Stone Ltd, (address as above)  
Tel: +44 (0)1246 554450 Fax: +44 (0)1246 220095  
[blockstone@realstone.co.uk](mailto:blockstone@realstone.co.uk)

Description: Highly fossilised, coarse grained Limestone  
Country of origin: UK  
Geological Type: Crinoidal Limestone of early Carboniferous age  
Colour: Various: Pale to dark grey, beige to buff, blue

As tested at STATS Ltd, St Albans in January 2002		
Test type	Method	Result
Apparent Density	EN 1936	2580 Kg/m <sup>3</sup>
Open Porosity	EN 1936	3.3 %
Flexural Strength, min	BSEN 12372	10.3 MPa
Abrasion	BSEN 1342	23.7 mm
Slip Resistance, wet	UK Slip Resistance Group	22
Roughness, µm	UK Slip Resistance Group	5.5

- Please note that stone is a natural product and all results are subject to variation.

**[www.blockstone.co.uk](http://www.blockstone.co.uk)**

*Directors J.P.Avent P.S.Bailey J.A.Gregory S.J.Wright*  
VAT No. 658 0923 15