

Ancaster Hard White

Specifying the stone

Quarry details

Ancaster Quarry, Quarry Farm,
Ancaster, Nr. Grantham,
Lincolnshire, England

Supplier

Block Stone Limited,
Wingerworth,
Derbyshire, S42 6RG

Contact

blockstone@realstone.co.uk



Limestone

Technical results

Description	Fine-grained jurassic limestone. Durable with good weathering qualities.	
Country of origin	UK	
Geological type	Jurassic limestone	
Colour	Cream white / occasional pink variations	
Density	2299 kg/m ³	
Compressive strength	25 MPa	BS EN 1926 (1999)
Water absorption	5.80 %	BS EN 13755 (2002)
Porosity	15.30 %	BS EN 1936 (1999)
Durability	Pass	BS EN 1341 (2001)
	Change in Flexural Strength 14.0 %	
Slip resistance	Dry 67 Wet 41	BS EN 1341 (2001)
Abrasion resistance	25.4mm	BS EN 1341 (2001)
	Moderate commercial use	
Saturation co-efficient	0.9 %	BRE 89

Please note that stone is a natural product and all results are subject to variation

Block sales

Block Stone Limited,
Bolehill Quarry,
Wingerworth, Chesterfield,
Derbyshire, S42 6RG,
England, UK

tel +44 (0)1246 554450
fax +44 (0)1246 220095
email blockstone@realstone.co.uk



www.blockstone.co.uk