

# Dukes

## Specifying the stone

### Quarry details

Dukes Quarry, Robinhood Lane,  
Whatstandwell, Derbyshire, UK

### Supplier

Block Stone Limited,  
Wingerworth,  
Derbyshire, S42 6RG

### Contact

[blockstone@realstone.co.uk](mailto:blockstone@realstone.co.uk)



s a n d s t o n e

## Technical results

Description	Medium-grained sandstone. Durable with good weathering qualities.	
Country of origin	UK	
Geological type	Carboniferous, millstone grit	
Colour	Dark and light purple / lilac / pink veining, light cream / buff / dark brown variations	
Water absorption	4.56 %	BS EN 13755
Porosity	13.40 %	BS EN 1936
Density	2250 kg/m <sup>3</sup>	
Compressive strength	50 MPa	BS EN 1926 (1999)
Durability	Tests indicate that failure due to frost action is unlikely	BS EN 1341 (2001)
Saturation co-efficient	0.69 %	
Acid immersion	Pass	BRE 141

Please note that stone is a natural product and all results are subject to variation

## Block sales

Block Stone Limited,  
Bolehill Quarry,  
Wingerworth, Chesterfield,  
Derbyshire, S42 6RG,  
England, UK

tel +44 (0)1246 554450  
fax +44 (0)1246 220095  
email [blockstone@realstone.co.uk](mailto:blockstone@realstone.co.uk)



[www.blockstone.co.uk](http://www.blockstone.co.uk)