

Block Stone Fine Buff

Specifying the stone

Quarry details

SiChuan province
P.R.China

Supplier

Block Stone Limited,
Wingerworth,
Derbyshire, S42 6RG

Contact

blockstone@realstone.co.uk



s a n d s t o n e

Technical results

| | | |
|-------------------------|---|-----------------|
| Description | Fine-grained sandstone without visible laminations. Durable with excellent weathering qualities. | |
| Country of origin | China | |
| Colour | Very clean light buff | |
| Density | 2230 kg/m ³ | BS EN 1936:1999 |
| Compressive strength | Dry 62 MPa | BS EN 1926:1999 |
| Water absorption | 5.10% | BS EN 13755 |
| Porosity | 5.10% | BS EN 1936 |
| Flexural strength dry | 5.5 MPa | BS EN 13161 |
| Freeze Thaw (48 cycles) | 4.6 MPa Pass. | BS EN 13161 |
| Slip resistance | Wet 81 Excellent Dry 91 Excellent | BSEN 1341:2000 |

Please note that stone is a natural product and all results are subject to variation

Block sales

Block Stone Limited,
Bolehill Quarry,
Wingerworth, Chesterfiel,
Derbyshire, S42 6RG,
England, UK

tel +44 (0)1246 554450
fax +44 (0)1246 220095
email blockstone@realstone.co.uk



www.blockstone.co.uk