

# Peak Moor

## Specifying the stone

### Quarry details

New Pillhough, Stanton in Peak,  
Derbyshire, UK

### Supplier

Block Stone Limited,  
Wingerworth,  
Derbyshire, S42 6RG

### Contact

[blockstone@realstone.co.uk](mailto:blockstone@realstone.co.uk)



s a n d s t o n e

## Technical results

Description	Medium-grained sandstone. Durable with good weathering qualities.	
Country of origin	UK	
Geological type	Carboniferous / Millstone grit	
Colour	Buff / Yellow some faint Pink / Brown iron intrusions	
Water absorption	10.49 %	BS EN 13755
Porosity	4.69 %	BS EN 1936
Density	2240 kg/m <sup>3</sup>	
Abrasion resistance	26.8	BS EN 1341 (2000)
	Moderate (offices etc)	
Compressive strength	71 MPa	BS EN 1926 (1999)
Slip resistance	Dry 94 Wet 79	BS EN 1341 (2000)
Flexural strength	7.64 MPa	BS EN 13161 (2001)
Durability	Pass. Change in flexural strength 0.80 %	BS EN 1341 (2001)
Acid immersion	Pass	BRE 141

Please note that stone is a natural product and all results are subject to variation

## Block sales

Block Stone Limited,  
Bolehill Quarry,  
Wingerworth, Chesterfield,  
Derbyshire, S42 6RG,  
England, UK

tel +44 (0)1246 554450  
fax +44 (0)1246 220095  
email [blockstone@realstone.co.uk](mailto:blockstone@realstone.co.uk)



[www.blockstone.co.uk](http://www.blockstone.co.uk)