

Scotch Buff

Specifying the stone

Quarry details

Gatherly Moor Quarry,
Gillingwest, Nr Richmond,
North Yorkshire, UK

Supplier

Block Stone Limited,
Wingerworth,
Derbyshire, S42 6RG

Contact

blockstone@realstone.co.uk



s a n d s t o n e

Technical results

Description	Medium-grained. Durable with good weathering qualities.	
Country of origin	UK	
Geological type	Carboniferous Westphalian sandstone	
Colour	Cream coloured with pervasive brown speckling, occasional brown lines, occasional small to large dark coloured patches	
Density	2130 kg/m ³	
Compressive strength	75.50 MPa	BS EN 1926 (1999)
Water absorption	5.70 %	BS EN 13755 (2002)
Porosity	19.80 %	BS EN 1936 (1999)
Durability	Tests indicate that failure due to frost action is unlikely	
Saturation co-efficient	0.6 %	BRE 89

Please note that stone is a natural product and all results are subject to variation

Block sales

Block Stone Limited,
Bolehill Quarry,
Wingerworth, Chesterfield,
Derbyshire, S42 6RG,
England, UK

tel +44 (0)1246 554450
fax +44 (0)1246 220095
email blockstone@realstone.co.uk



www.blockstone.co.uk