



Glasgow Cross Development

FURTHER REFERENCE BUILDINGS

- Aston Martin Factory – Gaydon (New Build)
- Pierce Bridge - Cliffe, North Yorkshire
- Greythwaits (Private Residence)
- Prestbury (New Build)
- Middleton Lodge - Middleton Tyas
- Harrogate Royal Baths - Yorkshire (New Build)
- Richmond Bridge - North Yorkshire
- Private Residence – Dunblane, Scotland (New Build)
- Croft Bridge - Crofton on Tees
- Earliest known use 1788

STONE TEST DATA: Tested at the BRE, Garston www.bre.co.uk

Test Type	Norm	Result
Absorption by Volume	BSEN 13755	5.70%
Porosity	BSEN 1936	19.80%
Density		2130 kg/m ³
Compressive Strength	BSEN 1926 (1999)	75.50 MPa
Durability	BSEN 1341:2001	Frost Damage Unlikely
Saturation co-efficient	BRE89	0.60%

TECHNICAL DETAILS:

- Geographical Type: Carboniferous, Westphalian
- Main Colour: Pale Buff
- Colour Variations: Beige/Brown to Dark Patches and Bedding Lines
- Texture: Medium Grain
- Availability: Contract up to 10,000m²
- Average Block Size: 1600L x 900W x 800Hmm
- Suggested Ashlar
- Module Size: 700L x 300Hmm

Colours in this brochure are as accurate as the printing process allows and actual sight of the material is strongly recommended.

SCOTCH BUFF SANDSTONE

This warm buff coloured sandstone derives its name from the fact that the quarry is situated very near to Scotch Corner in Richmondshire. Although the quarry has been worked in the past, there are not many historical records of where the stone has been used, other than in the local vicinity. Scotch Buff is a medium grained Gritstone, pale buff in colour with varying degrees of light to dark brown bed markings. Scotch Buff can be used on all facade applications and has been used recently on several new build projects.

BLOCK



STONE LIMITED

Bolehill Quarry, Wingerworth, Chesterfield, Derbyshire S42 6RG, England

Tel: +44 (0)1246 554450

Fax: +44 (0)1246 220095

Email: blockstone@realstone.co.uk

Web: www.blockstone.co.uk



Realstone
The Complete Natural Stone Service

Head Office

Realstone Limited

Wingerworth, Chesterfield, Derbyshire S42 6RG, England

Tel: +44 (0)1246 270244

Fax: +44 (0)1246 220095

Email: sales@realstone.co.uk

Web: www.realstone.co.uk

SCOTCH BUFF SANDSTONE