

Wattscliffe

Specifying the stone

Quarry details

Wattscliffe Quarry, Cliffe Lane,
Elton, Derbyshire, UK

Supplier

Block Stone Limited,
Wingerworth,
Derbyshire, S42 6RG

Contact

blockstone@realstone.co.uk



s a n d s t o n e

Technical results

Description	Medium-grained sandstone without visible laminations. Durable with good weathering qualities.	
Country of origin	UK	
Geological type	Carboniferous / Millstone grit	
Colour	Lilac / Grey	
Water absorption	4.75 %	BS EN 13755
Porosity	17.20 %	BS EN 1936
Density	2230 kg/m ³	
Compressive strength	56 MPa	BS EN 1926 (1999)
Durability	Tests indicate that failure due to frost action is unlikely	BS EN 1341 (2001)
Saturation co-efficient	0.67 %	
Acid immersion	Pass	BRE 141

Please note that stone is a natural product and all results are subject to variation

Block sales

Block Stone Limited,
Bolehill Quarry,
Wingerworth, Chesterfield,
Derbyshire, S42 6RG,
England, UK

tel +44 (0)1246 554450
fax +44 (0)1246 220095
email blockstone@realstone.co.uk



www.blockstone.co.uk